



RUVITEX INDUSTRY AD

Bulgaria, Ruse, 23A Tutrakan Blvd.

tel 082 840 510

13

041CPR2016-11-01

EN13956 : 2012

PVC flexible sheet for waterproofing RUVIMAT P08

/width 2m, length 30m, thickness 0.8 mm/

**For waterproofing of roofs, ponds
and artificial lakes**

Essential characteristics	Working parameters
1. Reaction to fire	Reaction to fire: Class F
2. Watertightness	Watertightness: Pass
3. Resistance to root penetration	Resistance to root penetration : NPD
4. Tear strength	Tear strength: - lengthwise - ≥ 80 N; - crosswise - ≥ 60 N;
5. Joint strength	Joint shear strength: ≥ 500 N/50mm; Joint peel strength: ≥ 120 N/50mm;

6. Tensile strength	Tensile strength: - lengthwise - $\geq 15 \text{ N/mm}^2$; - crosswise - $\geq 15 \text{ N/mm}^2$; Elongation: - lengthwise - $\geq 250\%$; - crosswise - $\geq 250\%$;
7. Foldability at low temperature	Foldability at low temperature : Not lower than or equal to -30°
8. Durability	Durability : NPD
9. Dangerous substances	Dangerous substances : NPD